

SPECIFICATIONS: Below Zero-PVC, Regular Body, Fast Set, Clear Cement

HCC Holdings, Inc.

4700 West 160th Phone: 800-321-9532
Cleveland, Ohio 44135 Website: www.oatey.com



BELOW ZERO-PVC, REGULAR BODY, FAST SET, CLEAR CEMENT Date: August 2017

- Regular bodied, fast set, clear cement for use on all schedules and classes of PVC pipe and fittings up to 6" diameter with interference fit.
- Can be used down to -10 °F (-23 °C)
- Lo VOC Solvent Cement that meets California South Coast Air Quality Management Districts (SCAQMD) 1168/316A or BAAQMD Method 40 requirements.
- Recommended for potable water, pressure pipe, conduit and DWV applications.
- Meets ASTM Standard D2564



APPROVALS & LISTINGS



Complies with NSF/ANSI 61 health effects requirements.

PHYSICAL PROPERTIES

Appearance:	Clear Liquid
Viscosity:	Min. 100 cps @73° F ± 2° F
Density:	7.40 ± 0.2 lbs/gallon
Shelf Life:	3 Years from Mfg. Date
Lap Shear Strength: (min. ASTM Standards)	
2 hours	250 psi
16 hours	500 psi
72 hours	900 psi
Set Up Time :	
30° F to 50° F	3 - 4 minutes
50° F to 70° F	2 - 3 minutes
70° F to 90° F	1 - 2 minutes