SPECIFICATIONS: PVC, Heavy Body, Slow Set, Gray Cement

HCC Holdings, Inc.

4700 West 160th
Cleveland, Ohio 44135

Phone: 800-321-9532
Website: www.Oatey.com

PVC, HEAVY BODY, SLOW SET, GRAY CEMENT

Date: August 2017

- Heavy bodied, slow set, gray cement for use on all schedules and classes of PVC pipe and fittings up to 15" diameter with interference fit.
- Lo VOC Solvent Cement that meets California South Coast Air Quality Management Districts (SCAQMD) 1168/316A or BAAQMD Method 40 requirements.
- Recommended for potable water, pressure pipe, conduit and DWV applications.
- Meets ASTM Standard D2564

APPROVALS & LISTINGS

PW-DWV-SW

Complies with NSF/ANSI 61 health effects requirements.

PHYSICAL PROPERTIES

Appearance:	Gray Liquid
Viscosity:	Min. 1600 cps @73° F ± 2° F
Density:	7.86 ± 0.2 lbs/gallon
Shelf Life:	3 Years from Mfg. Date
Lap Shear Strength: (min. ASTM Standards)	
2 hours	250 psi
16 hours	500 psi
72 hours	900 psi
Set Up Time :	
30° F to 50° F	5 - 6 minutes
50° F to 70° F	3 - 4 minutes
70° F to 90° F	1 – 2 minutes